

SHAPED PRODUCT	TZ-100
-----------------------	---------------

CLASSIFICATION UNE EN ISO 10081 UNE-EN 12475-4	Dense firebrick, chemistry-ceramic bonded. Base zircon. Group ZS 60
---	---

REFERENCE	932600	0914	667.RC	GROUP	FAMILY	STANDARD
				DE	65	

CHEMICAL AVERAGE ANALYSIS (Obs "A")

Al₂O₃	4,5	%
SiO₂	34,0	%
Fe₂O₃	0,5	%
CaO	0,1	%
ZrO₂	59,0	%

PHYSICAL PROPERTIES

Classification Temperature	1600	°C	
Aparent density (dense material)	3,50	Kg./dm ³	EN 993-1
Open porosity (dense material)	13,0	%	EN 993-1
Cold crushing strength:			
Dense material	450	Kg./cm ²	EN 993-5
Softening under load	1650	°C	EN ISO 1893
Sudden change in temperature	25	Cycles	PRE / R.5.1
Linear reversible dilation	1000 °C	0,70	%
Thermal conductivity	400 °C	2,30	W/m.K
	800 °C	2,40	W/m.K
	1200 °C	2,50	W/m.K

"A" Alternative method= Spectrometry by FRX

Applicable standards indicated. Other standards prior arrangements.
The technical characteristics represent the medium values from reconized essay methods of standard materials; they are under the normal variations of manufacturins and should not be considered like specifications.

EQUIVALENCES

1 N/mm² = 1 MPa = 10,2 kg/cm²
1 kg/cm² = 0,098 MPa = 0,098 N/mm²
1 W/mK = 0,86 kcal/mhK
1 Kcal/mK = 1,16 W/mK