

SHAPED PRODUCT	PI-70
-----------------------	--------------

CLASSIFICATION UNE EN ISO 10081 UNE-EN 12475-4	Cast and fired refractory shape of LCC concrete. Base andalusite. Class 1700°C
---	--

REFERENCE	930850	0915	164.IC	GROUP	FAMILY	STANDARD
				DE	30	

CHEMICAL AVERAGE ANALYSIS (Obs "A")

Al₂O₃	66,0	%
SiO₂	29,0	%
Fe₂O₃	1,2	%

PHYSICAL PROPERTIES

Classification Temperature	1710	°C	
Apparent density (dense material)	2,60	Kg./dm ³	EN 993-1
Open porosity (dense material)	20,0	%	EN 993-1
Cold crushing strength:			
Dense material	650	Kg./cm ²	EN 993-5
Softening under load	1650	°C	EN ISO 1893
Sudden change in temperature	30	Cycles	PRE / R.5.1
Linear reversible dilation	1000 °C	0,40	%
Thermal conductivity	400 °C	1,58	W/m.K
	800 °C	1,63	W/m.K
	1200 °C	1,79	W/m.K

OBSERVATIONS

Test of preformed pieces s/ EN 1402.7

"A" Alternative method= Spectrometry by FRX

Applicable standards indicated. Other standards prior arrangements.
The technical characteristics represent the medium values from recognized essay methods of standard materials; they are under the normal variations of manufacturers and should not be considered like specifications.

EQUIVALENCES

1 N/mm² = 1 MPa = 10,2 kg/cm²
1 kg/cm² = 0,098 MPa = 0,098 N/mm²
1 W/mK = 0,86 kcal/mhK
1 Kcal/mK = 1,16 W/mK