

SHAPED PRODUCT	PI-40
-----------------------	--------------

CLASSIFICATION UNE EN ISO 10081 UNE-EN 12475-4	Cast and fired refractory shape of LCC concrete. Base calcined refractory clay. Class 1400°C
---	--

REFERENCE	930750	0318	162.IC	GROUP	FAMILY	STANDARD
				DE	30	

CHEMICAL AVERAGE ANALYSIS (Obs "A")

Al ₂ O ₃	41,5	%
SiO ₂	53,5	%
Fe ₂ O ₃	1,5	%

PHYSICAL PROPERTIES

Classification Temperature	1430	°C	
Aparent density (dense material)	2,19	Kg./dm ³	EN 993-1
Open porosity (dense material)	16,0	%	EN 993-1
Cold crushing strength:			
Dense material	710	Kg./cm ²	EN 993-5
Softening under load	1460	°C	EN ISO 1893
Sudden change in temperature	25	Cycles	PRE / R.5.1
Linear reversible dilation	1000 °C	0,40	%
Thermal conductivity	400 °C	0,90	W/m.K
	800 °C	1,00	W/m.K
	1200 °C	1,30	W/m.K

OBSERVATIONS

Test of preformed pieces s/ EN 1402.7

"A" Alternative method= Spectrometry by FRX

Applicable standards indicated. Other standards prior arrangements.
The technical characteristics represent the medium values from reconized essay methods of standard materials; they are under the normal variations of manufacturins and should not be considered like specifications.

EQUIVALENCES

1 N/mm² = 1 MPa = 10,2 kg/cm²
1 kg/cm² = 0,098 MPa = 0,098 N/mm²
1 W/mK = 0,86 kcal/mhK
1 Kcal/mK = 1,16 W/mK