

**PRODUCT NOT CONFORMED****PYROFORM TIX-600**

<b>CLASSIFICATION</b> ISO 1927-1	Dense hydraulic LCC refractory concrete. Base silicon carbide. Application by casting and compaction by vibration. Class 1600°C
-------------------------------------	--

REFERENCE	936013	1216	682.RT	GROUP	FAMILY	STANDARD
				NC	13	

**AVERAGE CHEMICAL ANALYSIS (Obs "A")**

<b>Al<sub>2</sub>O<sub>3</sub></b>	21,0	%
<b>SiO<sub>2</sub></b>	17,0	%
<b>Fe<sub>2</sub>O<sub>3</sub></b>	0,4	%
<b>Sic</b>	60,0	%

**PHYSICAL PROPERTIES**

<b>Classification temperature</b>		1650	°C	ISO 1927-1
<b>Bulk density</b>	<b>Dry 110°C</b>	2,35	Kg./dm <sup>3</sup>	ISO 1927-6
<b>Open Porosity</b>	<b>Dry 110°C</b>	19,00	%	ISO 1927-6
<b>Compressive strenght</b>	<b>Dry 110°C</b>	380	Kg./cm <sup>2</sup>	ISO 1927-6
	<b>Stew 800°C</b>	390	Kg./cm <sup>2</sup>	ISO 1927-6
	<b>Stew 1200°C</b>	600	Kg./cm <sup>2</sup>	ISO 1927-6
<b>Reversible linear expansion</b>	<b>1000°C</b>	0,65	%	
<b>Thermal conductivity to average temperature</b>	<b>400°C</b>	9,51	W/m.K	ISO 1927-8
	<b>800°C</b>	8,24	W/m.K	ISO 1927-8
	<b>1200°C</b>	8,46	W/m.K	ISO 1927-8
<b>Kneaded water of</b>		6,0	%	ISO 1927-4

**OBSERVATIONS**

Thixotropic refractory concrete of high silicon carbide content, resistant to alcalis and dregs.  
Forced kneader and to vibrate well.  
Storage limit 8 months in dry warehouse.

"A" alternative Method = Spectrometry by FRX

The technical characteristics represent the obtained average values according to methods of tests recognized on standardized materials; they are put under the normal variations of manufacture and they do not have to be taken like specifications. The data of density and compressive strenght will not be valid for manual productions.

**EQUIVALENCES**

1 N/mm<sup>2</sup> = 1 MPa = 10,2 kg/cm<sup>2</sup>  
1 kg/cm<sup>2</sup> = 0,098 MPa = 0,098 N/mm<sup>2</sup>  
1 W/mK = 0,86 kcal/mhK  
1 Kcal/mK = 1,16 W/mK