

PRODUCT NOT CONFORMED**PYROMOR MP-160****CLASIFICATION
ISO 1927-1**Refractory liquid for meetings of hardening to the air.
Base silicify-aluminous and bauxite.
Application with spatula.
Class 1600°C

REFERENCE	936483	1117	1000.RT	GROUP	FAMILY	STANDARD
				NC	35	

AVERAGE CHEMICAL ANALYSIS (Obs "A")

Al₂O₃	55,0	%
SiO₂	35,0	%
Fe₂O₃	1,0	%
CaO	0,5	%

PHYSICAL PROPERTIES

Classification temperature	1600	°C	ISO 1927-1
Open Porosity	Dry 110° C	26,00	% ISO 1927-6

OBSERVATIONSChemical setting to the air.
Ready for its use.**"A" alternative Method = Spectrometry by FRX**

The technical characteristics represent the obtained average values according to methods of tests recognized on standardized materials; they are put under the normal variations of manufacture and they do not have to be taken like specifications. The data of density and compressive strenght will not be valid for manual productions.

EQUIVALENCES

1 N/mm² = 1 MPa = 10,2 kg/cm²
 1 kg/cm² = 0,098 MPa = 0,098 N/mm²
 1 W/mK = 0,86 kcal/mhK
 1 Kcal/mK = 1,16 W/mK