PRODUCT NOT CONFORMED

PYROFORM TIX-900

CLASIFICATION	Dense hydraulic LCC refractory concrete.
ISO 1927-1	Base silicon carbide.
	Aplication by casting and compaction by vibration.
	Class 1600°C

REFERENCE	936026 0719	0719	869.RT	GROUP	FAMILY	STANDARD
TIET ETTENOE		000.111	NC	13	017.11.157.11.15	

AVERAGE CHEMICAL ANALYSIS (Obs "A")

AI2O3	4,5	%
SiO2	8,3	%
Fe2O3	0,2	%
Sic	82,6	%

PHYSICAL PROPERTIES

Classification temperature	1600	°C	ISO 1927-1	
Bulk density	Dry 110°C	2,50	Kg./dm3	ISO 1927-6
Open Porosity	Dry 110°C	20,00	%	ISO 1927-6
opon i ciccity	Stew 800°C	17,00	%	ISO 1927-6
	Dry 110°C	1000	Kg./cm2	ISO 1927-6
Compressive strenght	Stew 800°C	920	Kg./cm2	ISO 1927-6
	Stew 1200°C	1050	Kg./cm2	ISO 1927-6
Subsidence under	T2	1550	°C	ISO 1927-6
Reversible linear expansion	1000°C	0,60	%	
Permanent Linear Variation	1000°C	- 0,25	%	ISO 1927-6
	400°C	8,60	W/m.K	ISO 1927-8
Thermal conductivity to average temperature	800°C	8,23	W/m.K	ISO 1927-8
	1200°C	8,07	W/m.K	ISO 1927-8
Kneaded water of		7,0	%	ISO 1927-4

OBSERVATIONS

Thixotropic refractory concrete of very high content in silicon carbide.

Very resistant to alcalis. Attention to the oxidating atmosphere.

To knead in forced kneader. To vibrate well.

Storage limit 8 months in dry warehouse.

"A" alternative Method = Spectrometry by FRX

The technical characteristics represent the obtained average values according to methods of tests recognized on standardized materials; they are put under the normal variations of manufacture and they do not have to be taken like specifications. The data of density and compressive strength will not be valid for manual productions.

EQUIVALENCES

- 1 N/mm2 = 1 MPa = 10,2 kg/cm2
- 1 kg/cm2 = 0,098 MPa = 0,098 N/mm2
- 1 W/mK = 0,86 kcal/mhK
- 1 Kcal/mK = 1,16 W/mK